

Test recycleability at Fiskeby

| | | | |
|---------------------------|---|----------------|--------------------------|
| Client: | FibreStrap | Item: | Strings from Fibrestraps |
| | EVLIR International AB Birger Jarlsgatan 41A, 6 tr 111 45 Stockholm | | |
| | | VAT nr: | |
| Reference client: | Sigrid Svedberg | | |
| Reference Fiskeby: | Torbjörn Gustavsson | | |

| Type of test | Test contains | Purpose of test |
|--------------|---|--------------------------------------|
| Sample sheet | Pulping, sample sheet, statement, report with picture and mail. | Assessing recycleability at Fiskeby. |

| | |
|----------------------|---|
| Pulping: | Aprox. 10 g of the string part of fibrestraps were dissolved in a lab pulper. The string part dissolved without proplems. |
| Sample sheet: | It was possible to make sheets from the pulp. The sheets were quite evenly formed. No major signs of shives (= not fully dissolved fibres). The fibres in the sheets bonded quite well to each other. |
| Statement: | The string part of the FibreStrap is recycleable at Fiskeby. |

